

Product Description

AQUENCE PL 165 provides the following product characteristics:

Technology	PVAc Dispersion
Product Type	Water based adhesive
Application	Assembly
Appearance	White liquid Transparent after drying

Application Areas

- Can be used for HPL /Veneer / Paper lamination on MDF, Particle board, & Plywood
- Suitable for Cold and Hot press.

Product properties

- Medium viscosity
- Gives transparent, tough-elastic glue joint
- High water resistance one component adhesive.

Technical Data

Viscosity :	12000 - 18000 cps
(BF RVF 5/10/27 °C)	
Solid :	40 ± 2 %

Cleaning

Equipment used to apply the glue may be cleaned easily using cold or Luke-warm water before the adhesive has dried hard. Hard dried glue remnants have to be removed mechanically.

Storage

Store in a dry place where the temperature is between 20 °C and 40 °C. Don't expose to sunlight.

Shelf Life

Shelf-life (in unopened original packaging), 6 months.

Standard Package 26 and 50 kg

Classification:

Please refer to the corresponding **safety data sheets** for details on:

Hazardous Information**Transport Regulations****Safety Regulations****Additional Information****Disclaimer:**

The information provided herein, especially recommendations for the usage and application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regards to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

This datasheet replaces all former versions.

Preparation date: June 2021